

Sherd ID	Na <sub>2</sub> O	MgO	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	K <sub>2</sub> O	CaO	Sc†	TiO <sub>2</sub>	V†	Cr <sub>2</sub> O <sub>3</sub>	MnO	Fe <sub>2</sub> O <sub>3</sub>	CoO	NiO	Zn†	Sr†	La†	Ce†
C-LH 17	1.33	3.75	18.3	61.4	2.18	14.09	13	0.870	148	0.030	0.151	8.55	0.003	0.021	81	306	37	64
C-PG 22	0.89	2.33	14.2	53.1	1.85	15.86	18	0.655	130	0.028	0.226	6.59	0.004	0.018	122	352	29	60
C-PG 58	0.80	5.30	15.9	60.4	3.09	7.99	17	0.948	128	0.084	0.104	7.37	0.004	0.047	116	189	33	72
C-PG 93	1.08	3.91	15.1	56.0	2.30	14.03	13	0.760	120	0.033	0.128	7.27	0.003	0.021	95	347	30	72
C-LacPG 2	0.99	3.26	19.2	68.3	3.22	8.93	16	0.890	157	0.041	0.092	7.60	0.003	0.029	127	254	33	81
C-LacPG 9	1.13	2.12	23.2	74.6	3.27	6.90	15	1.017	181	0.030	0.065	10.11	0.003	0.017	179	175	32	98
C-LacPG 19	0.93	3.67	20.3	64.3	3.30	8.14	14	0.857	157	0.040	0.108	9.50	0.004	0.029	138	225	40	96
C-LacPG 40	1.06	2.47	19.7	67.5	3.01	9.07	14	0.917	137	0.038	0.076	7.46	0.004	0.028	136	210	43	117
C-LacPG 44	1.18	2.47	21.2	71.3	3.10	8.04	14	1.043	135	0.028	0.067	7.16	0.003	0.023	141	286	34	19
C-LacPG 46	1.11	2.58	16.3	59.5	3.60	6.08	25	0.785	174	0.031	0.077	6.31	0.004	0.021	129	236	34	68
C-LacPG 53	0.97	2.05	19.5	65.3	2.88	8.06	13	1.016	148	0.026	0.056	7.54	0.003	0.013	145	182	34	89
C-LacPG 54	1.11	2.21	19.4	60.5	2.98	6.89	19	1.077	123	0.020	0.077	8.04	0.004	0.013	121	229	56	106
C-LacPG 57	1.08	2.54	20.5	68.1	3.18	7.83	15	0.895	159	0.034	0.081	9.56	0.003	0.022	145	190	33	88
C-LacPG 58	2.04	3.99	24.1	103.2	4.09	18.30	31	1.275	206	0.040	0.187	10.24	0.005	0.025	136	370	42	79
C-LacPG 67	1.01	3.41	19.3	67.3	3.20	9.86	28	0.898	189	0.040	0.098	7.65	0.005	0.025	129	266	40	78
C-LacPG 69	0.98	3.23	18.6	65.2	3.10	8.88	14	0.859	152	0.042	0.100	7.54	0.004	0.028	137	232	50	94
C-LacPG 87	1.00	3.65	18.9	64.3	3.02	13.47	12	0.890	149	0.033	0.208	9.19	0.004	0.022	111	227	30	105
C-LacPG 96	0.91	3.38	17.1	64.4	3.48	6.75	18	0.949	150	0.041	0.105	7.79	0.004	0.025	116	216	42	117
C-LacPG 100	0.49	1.36	17.2	70.3	2.55	0.42	17	1.232	139	0.031	0.103	7.90	0.003	0.017	125	63	58	139
C-LacPG 106	1.10	2.25	22.6	69.3	3.19	7.03	14	1.106	154	0.028	0.061	7.94	0.004	0.016	163	192	40	78
C-LacPG 110	0.91	3.66	17.4	62.8	3.40	7.90	20	0.906	166	0.049	0.134	7.78	0.005	0.038	111	210	31	111
C-LacPG 117	1.11	2.71	19.3	70.0	3.17	7.32	13	0.988	141	0.034	0.084	7.74	0.004	0.025	134	223	48	116
C-LacPG 121	1.16	2.41	20.0	58.3	3.39	4.80	116	1.136	132	0.023	0.062	7.42	0.003	0.013	140	197	47	109
C-LacPG 134	1.00	3.01	15.6	54.4	3.59	7.20	24	0.685	163	0.033	0.093	7.35	0.004	0.025	98	237	33	46
C-LacPG 139	0.99	2.51	16.9	68.4	2.91	6.88	9	0.798	127	0.039	0.075	5.93	0.004	0.025	100	196	48	97
C-LacPG 143	0.97	2.94	17.9	63.9	3.12	7.92	21	0.805	136	0.040	0.092	7.08	0.004	0.025	122	232	32	62
C-EG 21	0.70	2.56	15.3	70.5	2.36	14.94	20	0.803	151	0.032	0.179	7.07	0.004	0.019	145	318	31	58
C-EG 23	1.33	2.65	14.8	62.8	2.56	12.33	11	0.797	112	0.028	0.120	7.08	0.003	0.016	93	210	32	75
C-EG 24	1.33	2.89	16.2	66.7	2.94	12.83	12	0.840	110	0.031	0.128	7.58	0.003	0.018	89	232	29	77
C-EG 40	1.49	3.84	15.3	53.4	1.93	14.79	14	0.876	147	0.031	0.129	7.65	0.003	0.022	83	422	27	117
C-EG 50	0.58	4.43	13.4	56.8	2.29	9.17	22	0.758	123	0.075	0.079	6.82	0.004	0.043	119	187	24	52

Sherd ID	Na <sub>2</sub> O	MgO	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	K <sub>2</sub> O	CaO	Sc†	TiO <sub>2</sub>	V†	Cr <sub>2</sub> O <sub>3</sub>	MnO	Fe <sub>2</sub> O <sub>3</sub>	CoO	NiO	Zn†	Sr†	La†	Ce†
C-EG 51	1.26	3.54	16.2	57.5	2.37	13.39	23	0.801	163	0.028	0.140	7.84	0.003	0.018	87	284	30	69
C-EG 53	1.10	3.26	17.1	63.1	2.67	13.96	8	0.814	137	0.031	0.147	8.00	0.003	0.017	109	285	30	82
C-EG 59	1.34	2.86	15.1	66.3	2.90	11.44	23	0.790	147	0.030	0.125	7.07	0.003	0.016	85	283	31	52
C-EG 71	0.53	1.78	10.9	40.5	1.92	4.57	15	0.565	109	0.028	0.049	4.49	0.002	0.026	75	129	19	37
C-EG 104	1.31	2.76	13.1	54.5	2.72	13.99	20	0.713	134	0.024	0.102	5.57	0.003	0.016	81	302	28	69
C-MG 2	0.42	2.58	15.0	53.4	2.21	15.61	18	0.831	106	0.027	0.189	7.99	0.005	0.019	148	463	65	105
C-MG 44	1.46	2.67	14.3	62.9	2.82	9.81	21	0.723	137	0.025	0.115	6.40	0.004	0.018	79	272	36	61
C-MG 45	1.34	2.70	15.8	65.5	2.71	12.37	11	0.866	121	0.029	0.120	7.28	0.003	0.018	94	201	29	75
C-MG 50	0.53	2.63	16.5	65.3	2.52	12.08	136	0.841	138	0.030	0.267	8.01	0.004	0.021	147	278	37	99
C-MG 64	0.49	2.94	15.6	60.7	2.80	11.52	17	0.890	160	0.034	0.186	7.68	0.005	0.026	141	265	35	102
C-MG 65	0.53	2.61	15.5	55.8	2.66	15.84	14	0.821	109	0.028	0.236	7.46	0.004	0.022	118	354	36	112
C-MG 70	0.54	2.17	20.8	78.2	2.47	18.46	13	0.780	168	0.041	0.244	11.17	0.005	0.026	141	348	61	89
C-MG 73	0.55	2.59	15.8	56.1	2.70	10.91	17	0.914	120	0.026	0.258	7.03	0.004	0.021	115	298	45	116
C-MG 76	0.84	3.01	12.8	58.9	2.26	13.68	14	0.748	107	0.029	0.278	6.92	0.005	0.022	145	330	31	76
C-MG 100	0.49	2.78	16.3	59.1	2.70	10.73	17	0.902	149	0.029	0.243	8.10	0.004	0.024	150	280	40	114
C-LG 53	0.56	2.76	15.0	61.1	2.66	10.93	16	0.930	142	0.029	0.305	7.66	0.005	0.022	143	297	39	119
C-LG 54	1.46	2.91	18.7	81.0	2.70	12.40	9	0.776	142	0.037	0.193	10.58	0.004	0.022	119	222	21	66
C-LG 65	0.52	2.71	17.2	60.4	2.81	13.31	16	0.905	128	0.030	0.282	8.35	0.005	0.026	129	318	45	111
C-LG 76	0.45	2.25	13.2	51.7	2.23	16.57	12	0.665	112	0.024	0.224	7.62	0.003	0.017	122	333	29	102
C-LG 85	0.49	3.21	17.3	58.0	2.90	9.49	19	1.011	149	0.032	0.176	7.61	0.005	0.026	120	251	46	122
C-LG 96	0.85	3.32	15.4	59.2	3.29	9.38	18	0.807	124	0.045	0.097	7.50	0.004	0.032	105	307	36	92
C-LG 111	0.50	2.43	18.9	75.3	2.60	14.83	13	0.740	188	0.043	0.437	11.24	0.006	0.028	161	239	32	86
C-LG 112	0.66	2.41	13.4	59.9	2.28	14.79	14	0.825	127	0.030	0.191	7.40	0.005	0.020	108	329	36	96
C-LG 138	0.49	2.81	14.9	55.7	2.74	12.73	17	0.905	116	0.029	0.228	7.43	0.005	0.025	116	353	43	137
C-LG 139	1.53	3.43	14.6	60.1	2.43	11.27	14	0.932	90	0.025	0.115	6.51	0.003	0.016	66	308	32	116
C-LG 169	0.54	2.62	15.6	59.0	2.43	14.70	18	0.852	116	0.025	0.269	7.62	0.005	0.019	101	341	50	93
C-LG 178	0.40	2.90	16.3	57.3	2.82	10.28	20	0.916	120	0.027	0.362	8.28	0.005	0.023	127	262	62	93
C-LG 195	0.43	2.78	17.5	67.1	2.68	15.67	13	0.768	156	0.032	0.265	9.73	0.005	0.026	141	301	25	89
C-LG 200	1.42	2.76	18.0	76.8	2.42	14.14	9	0.759	126	0.034	0.169	9.00	0.003	0.019	93	218	16	91
C-LG 212	0.90	2.62	16.7	60.6	2.01	14.63	18	0.729	155	0.030	0.322	8.64	0.004	0.025	117	268	33	94
C-SG 18	0.50	1.96	11.4	50.8	1.99	19.17	12	0.669	103	0.023	0.211	6.33	0.004	0.017	109	435	29	82

**Table 1.a.** Analysis data for the chemical composition of sampled pottery from Tegea.

All analyses were recoded in oxide weight percentage; trace elements with very low composition contents were recorded in parts-per-million (ppm) and indicated by the † symbol.